

检 测 报 告

TEST REPORT



扫一扫 查真伪



扫一扫关注我们

报告编号: RTS23R36720TX

Report No.:

送检企业: 东阳市晶日金银线有限公司

Applicant:

检验类别: 委托检测

Test Category:

浙江瑞易检测技术有限公司

ZHEJIANG RTS TEST CO., LTD.





检测报告

报告编号: RTS23R36720TX

报告日期: 2023-12-23

客户名称: 东阳市晶日金银线有限公司

地址: 浙江省东阳市巍山镇余店村

产品名称: 金银线编绳

颜色: 正金

以上检测信息由申请人提供。

接收日期: 2023年12月21日

检测日期: 2023年12月21日~2023年12月23日

样品描述: 金银线编绳

检测项目: 根据客户要求对来样做以下项目: 甲醛含量, pH值, 可分解致癌芳香胺染料(偶氮染料), 异味, 耐水色牢度, 耐汗渍色牢度, 耐摩擦色牢度, 耐唾液色牢度。

判定依据: GB 18401-2010 《国家纺织产品基本安全技术规范》 A类

检测结论: 依据上述检测依据, 对所送检样品进行检测, 所检项目的检测结果均符合判定依据要求。

审核人:

张琳晓

签发人:

签发日期:

2023-12-23



检测报告

报告编号: RTS23R36720TX

报告日期: 2023-12-23

一、检测结果概要:

序号	检测项目	判定依据	结论
检测点位描述: 001:金色线编绳			
1	甲醛含量	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
2	pH值	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
3	可分解致癌芳香胺染料	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
4	异味	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
5	耐水色牢度	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
6	耐汗渍色牢度	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
7	耐摩擦色牢度	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合
8	耐唾液色牢度	GB 18401-2010 国家纺织产品基本安全技术规范 A类	符合

- 注 1“符合”表示检测结果符合客户或标准要求,“不符合”表示检测结果不符合客户或标准要求;
2“不适用”表示该项目没有符合标准要求测试的材料、部位,或该项目不符合标准要求的测试条件;
3“未检出”表示小于检出限(方法检出限),除非客户要求,本报告检测结果及符合性判定未考虑检测结果的不确定度。

二、检测结果:

1. 甲醛含量: (单位: mg/kg)

检测方法: GB/T 2912.1-2009, 采用 UV-VIS 进行检测。

序号	检测项目	CAS 号	检出限	限值	结果
					001
1	甲醛含量	50-00-0	20	≤ 20	未检出
结论					符合

2. pH 值

检测方法: GB/T 7573-2009, 采用 pH 计进行分析。

测试条件: 萃取介质: 0.1 mol/L 氯化钾溶液。

萃取介质的 pH 值 5.0~7.5。

提取液温度 22 + 2℃。

序号	检测项目	CAS 号	检出限	限值	结果
					001
1	pH 值	--	--	4.0~7.5	6.5
结论					符合

3. 可分解致癌芳香胺染料: (单位: mg/kg)

检测方法: GB/T 17592-2011, 采用 GC-MS 进行测定

序号	检测项目	CAS 号	检出限	限值	结果
					001
1	邻甲苯胺	95-53-4	5	≤ 20	未检出
2	2,4-二甲基苯胺	95-68-1	5	≤ 20	未检出
3	2,6-二甲基苯胺	87-62-7	5	≤ 20	未检出
4	邻氨基苯甲醚	90-04-0	5	≤ 20	未检出
5	对氯苯胺	106-47-8	5	≤ 20	未检出
6	2-甲氧基-5-甲基苯胺	120-71-8	5	≤ 20	未检出
7	2,4,5-三甲基苯胺	137-17-7	5	≤ 20	未检出
8	4-氯-邻甲苯胺	95-69-2	5	≤ 20	未检出
9	2,4-二氨基甲苯	95-80-7	5	≤ 20	未检出
10	2,4-二氨基苯甲醚	615-05-4	5	≤ 20	未检出
11	2-萘胺	91-59-8	5	≤ 20	未检出

12	5-硝基-邻甲苯胺	99-55-8	5	≤ 20	未检出
13	4-氨基联苯	92-67-1	5	≤ 20	未检出
14	4-氨基偶氮苯	60-09-3	5	≤ 20	未检出
15	4,4'-二氨基二苯醚	101-80-4	5	≤ 20	未检出
16	联苯胺	92-87-5	5	≤ 20	未检出
17	4,4'-二氨基二苯甲烷	101-77-9	5	≤ 20	未检出
18	邻氨基偶氮甲苯	97-56-3	5	≤ 20	未检出
19	3,3'-二甲基-4,4'-二氨基二苯甲烷	838-88-0	5	≤ 20	未检出
20	3,3'-二甲基联苯胺	119-93-7	5	≤ 20	未检出
21	4,4'-二氨基二苯硫醚	139-65-1	5	≤ 20	未检出
22	3,3'-二氯联苯胺	91-94-1	5	≤ 20	未检出
23	4,4'-亚甲基-二-(2-氯苯胺)	101-14-4	5	≤ 20	未检出
24	3,3'-二甲氧基联苯胺	119-90-4	5	≤ 20	未检出
结论					符合

4. 异味

检测方法: GB 18401-2010, 第 6.7 章节

材料号	要求	结果	判定
001	无异味	无异味	符合

5. 耐水色牢度: (单位: 级)

检测方法: GB/T 5713-2013

材料号	要求	结果		判定
001	变色 ≥ 3-4 沾色 ≥ 3-4	变色	4-5	符合
		沾色-醋纤	4-5	
		沾色-棉	4-5	
		沾色-锦纶	4-5	
		沾色-聚酯纤维	4-5	
		沾色-腈纶	4-5	
		沾色-羊毛	4-5	

说明: 色牢度级别根据 5 级灰卡进行评定, 1 级表示最差, 5 级表示最好。

6. 耐汗渍色牢度: (单位: 级)

检测方法: GB/T 3922-2013

材料号	要求	结果		判定
001	碱性: 变色 \geq 3-4	变色	4-5	符合
		沾色-醋纤	4-5	
	碱性: 沾色 \geq 3-4	沾色-棉	4-5	
		沾色-锦纶	4-5	
		沾色-聚酯纤维	4-5	
		沾色-腈纶	4-5	
		沾色-羊毛	4-5	
		酸性: 变色 \geq 3-4	变色	
	酸性: 沾色 \geq 3-4	沾色-醋纤	4-5	
		沾色-棉	4-5	
		沾色-锦纶	4-5	
		沾色-聚酯纤维	4-5	
		沾色-腈纶	4-5	
		沾色-羊毛	4-5	

说明: 色牢度级别根据 5 级灰卡进行评定, 1 级表示最差, 5 级表示最好。

7. 耐摩擦色牢度: (单位: 级)

检测方法: GB/T 3920-2008

材料号	要求	结果		判定
001	干摩擦 \geq 4	干摩擦-长度方向	4-5	符合

说明: 色牢度级别根据 5 级灰卡进行评定, 1 级表示最差, 5 级表示最好。

8. 耐唾液色牢度: (单位: 级)

检测方法: GB/T 18886-2019

材料号	要求	结果		判定
001	变色 \geq 4 沾色 \geq 4	变色	4-5	符合
		沾色-醋纤	4-5	
		沾色-棉	4-5	
		沾色-锦纶	4-5	
		沾色-聚酯纤维	4-5	
		沾色-腈纶	4-5	
		沾色-羊毛	4-5	

说明: 色牢度级别根据 5 级灰卡进行评定, 1 级表示最差, 5 级表示最好。

三、检测点位描述:

001: 金色线编绳

四、样品照片:



----- 报告结束 -----

浙江瑞易检测技术有限公司
章。

声 明

Statement

- 1.本检测报告首页所列信息中除接收日期、检测日期、样品描述和检测结论外，均由委托方提供，委托方对样品的代表性和资料的真实性负责，本机构不承担任何相关责任。
The information as listed on the first page of this test report was all provided by the client except the sample from, date received, test period, test results and test conclusion. The client shall be responsible for the representativeness of sample and authenticity of materials, for which RTS shall bear no responsibilities.
- 2.本检测报告以实测值进行符合性判定，未考虑不确定度所带来的风险，特别约定、标准或规范中有明确规定的除外。此种判定方式所带来的风险由客户自行承担，本机构不承担相关责任。
The judgment method of determining the conformity in this test report is according to the measured value without considering the risk caused by uncertainty, unless otherwise clearly stipulated in special agreement, standard or specification. The client shall assume the risk caused by the judgment method, and RTS shall not bear related responsibilities.
- 3.检测报告无签发人签字及“检验检测专用章”无效，未经本机构书面同意，不得整体或部分复制本报告。
The test report is effective only with both signature and specialized stamp. Without written approval of RTS, this report can't be reproduced in full or in part.
- 4.本检测报告的检测结果仅对送测样品负责，未加盖资质认定标志的检测报告不对社会具有公证证明作用，对于检测数据、结果的使用，所产生的直接或间接损失及一切法律后果，本机构不承担任何经济和法律后果。
This test data is only responsible for the tested sample. The data and results provided by the report without CMA accreditation are not to prove to the society, and RTS is not responsible for any economic and legal responsibility for the use of the test data, the direct or indirect losses resulting from the use of the test and all legal consequences.
- 5.本检测报告中检测项目标注有下划线则该项目不在本机构资质认定和认可能力范围内，该项目检测结果仅作为客户委托、科研、教学或内部质量控制等目的使用。
The underlined test item in the report is out of the scope of CMA accreditation. The test result only used for client's requirement, scientific researching ,teaching or internal quality control.
- 6.该测试报告的支持数据和信息本机构保存 6 年。个别评审机构有特别要求的，检测数据和报告的保存期可依情况变动。一旦超过上述提交的保存期限，数据和信息将被处理掉。任何情况下，本公司不必提供任何被处理的过期数据或信息。即使本公司事先被告知可能会发生相关的损害，本公司在任何情况下也不必承担任何损害，包括（但不限于）补偿性赔偿、利润损失、数据遗 失、或任何形式的特殊损害、附带损害、间接损害、从属损害或任何违反约定、违反承诺、侵权（包括疏忽）、产品责任或其他原因的惩罚性损害。
Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.
- 7.其它声明请查阅报告页脚及书面报告末页。
For other statements, please refer to the footer of the report.

RTS